

INSTRUCTIONS FOR APPLICATION of Ognyanovo K Hydrated Lime

Unbearing masonries mortar - for a ready mortar of appr. 0,300 m³

Hydrated lime	Cement PC 35	Dry sand	Water
1 bag (25 kg)	1 bag (50 kg)	27 buckets x 10 l (0,270 m ³)	75 l

Bearing masonries mortar - for a ready mortar of appr. 0,200 m³

Hydrated lime	Cement PC 35	Dry sand	Water
1/2 bag (15 kg)	1 bag (50 kg)	21 buckets x 10 l (0,210 m ³)	55 l

Internal plasters mortar - for a ready mortar of appr. 0,300 m³

Hydrated lime	Cement PC 35	Dry sand	Water
1 bag (25 kg)	4/5 bag (42 kg)	26 buckets x 10 l (0,260 m ³)	70 l

External plasters mortar - for a ready mortar of appr. 0,300 m³

Hydrated lime	Cement PC 35	Dry sand	Water
1 bag (25 kg)	1 ¼ bag (63 kg)	28 buckets x 10 l (0,280 m ³)	75 l

The hydrated lime, the cement and the sand are initially mixed in dry state, adding portions of water and stirring constantly until a convenient laying consistency is obtained.

The ready mortars can be put immediately into use. The ready mortar must not be used later than 4 hours from its preparation.